



TEXICRYL 13-308

Carboxylated acrylic copolymer emulsion

INTRODUCTION Texicryl 13-308 is an alkali soluble emulsion designed as a thickener for waterbased formulations

CHARACTERISTICS (Not to be taken as a specification)

Solids Content	%	30
Viscosity at 25°C (Brookfield RVT, Spindle 2,100 rpm)	mPa s	25
pH		3
Specific gravity at 25°C		1.07
Minimum film formation temperature*	°C	0
Particle size	nm	200
Glass transition temperature	°C	57

* Determined by metal bar with temperature gradient.

APPLICATIONS

Used in the formulation of ceramic tile adhesives, paints and waterborne coating systems.

PACKAGING

Texicryl 13-308 is supplied in drums or IBC's. Bulk deliveries are by road tanker.

STORAGE

Texicryl 13-308 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.2

Scott Bader Company Limited
Wollaston, Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

