



TEXICRYL 13-309

Carboxylated acrylic copolymer emulsion

INTRODUCTION

Texicryl 13-309 is a carboxylated acrylic copolymer emulsion designed for use as a thickener in emulsion paints and for thickening various adhesive compounds.

CHARACTERISTICS (Not to be taken as a specification)

| | | |
|--|-------|----|
| Solids Content | % | 35 |
| Viscosity at 25°C (Brookfield RVT, Spindle 2, 100 rpm) | mPa s | 50 |
| pH | | 3 |
| Minimum film formation temperature* | °C | 10 |
| Glass transition temperature | °C | 42 |

* Determined by metal bar with temperature gradient.

APPLICATIONS

Thickener for use in artist’s paints, adhesives and textile coatings. Texicryl 13-309 helps balance rheological properties of a paint and aids application / flow properties.

PACKAGING

Texicryl 13-309 is supplied in drums and 1 tonne IBC’s. Bulk deliveries are supplied by road tanker.

STORAGE

Texicryl 13-309 can be stored in containers supplied and protected from frost and extended exposure to direct sunlight

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No. 3

Scott Bader Company Limited
Wollaston, Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

